



RESISTANCE TO CHEMICALS

ASTM F925

2.5mm | 20mil

5 minute ratings

24 hour ratings

staining agent	surface dulling	surface attack	color change	surface dulling	surface attack	color change
5% acetic acid	0	0	0	0	0	0
70% isopropyl alcohol	0	0	0	0	0	0
mineral oil	0	0	0	0	0	0
5% sodium hydroxide	0	0	0	0	0	0
sulfuric acid	0	0	0	0	0	0
5% hydrochloric acid	0	0	0	0	0	0
5% ammonia	0	0	0	0	0	0
5.25% sodium hypochlorite	0	0	0	0	0	0
5% phenol	0	0	0	0	0	0
bleach	0	0	0	0	0	0
gasoline	0	0	0	0	0	0
olive oil	0	0	0	0	0	0
noble brio cream cleanser	0	0	0	0	0	0
ecolab milkro quat	0	0	0	0	0	0
kerosene	0	0	0	0	0	0

0 - no change

- 1 slight change2 moderate change
- 3 severe change

