



WOVEN

Technical Specifications

Sizes

Size	Thickness	Pcs/Carton	Sqft/Carton	Lbs/Carton
25 cm x 100 cm (9.84 in x 39.37 in)	3.0 mm	16 pcs	43.03 sqft	44.08 lbs

Testing

Test Item		Standard	Results
Level of use		ISO 10874	33, Heavy commercial
Fraying		ISO 10833	Frayproof
Thermal resistance		ISO 8302	0.02m²K/W
Castor chair resistance		ISO 4918	No damage
Dimensional stability		ISO 23999 EN 986	≤ 0.10% (Norm: ≤ 0.25%) Passed
Fire resistance		EN 13501-1	Bfl -s1
Indoor air quality			Low VOC (floor score certified)
Underfloor heating		EN 12524	Suitable
Light fastness		ISO 105-B02	≥ 6
Slip resistance		ASTM E303 EN 13893	R11, Suitable for wet and dry environments DS
Flexibility		ISO 24344	Passed
Impact sound insulation		ISO 10140-3	9dB
Body Voltage		EN 1815	≤ 2KV
Squareness & Straightness		ISO 24342 ASTM F2055	No deviation ≤ 0.01 in
Residual indentation		ISO 24343-1 ASTM F1914	≤ 0.1mm < 8%
Resistance to chemicals		ISO 26987 ASTM F925	No Defects No Defects

Caution

Condition in at least 19°C (67°F) or the normal temperature of the room where the product is to be laid, for at least 48 hours before installing. Cartons must be stacked less than 5 high and tiles removed 30 minutes before use. The site conditions must be maintained during installation and for at least 48 hours after completion. Evo Floors, LLC will not accept claims where these instructions have not been followed.

Certification



Please visit www.evofloors.com for detailed installation / maintenance guides and technical information.